



KURALTEX BL 314

Transparent protective agent

- Protects surfaces without changing the appearance
- Excellent dirt repellent action
- Resistant to UV radiation and weather
- Flexible layer does not crack or tear
- For aluminium, plastics, and coated metals

KURALTEX BL 314

DESCRIPTION

A concentrated protective agent based on acrylic copolymers and polythene additives for anodised aluminium, coated metal surfaces, and a variety of plastics.

RECOMMENDED USE

Kuraltex BL 314 is suitable as a limited-lifespan protection for anodised aluminium, coated metal surfaces, and plastics.

RECOMMENDED SYSTEM

First layer : Kuraltex BL 314 of Kuraltex Primer

Second layer : Kuraltex BL 314

Remove with : Vetclean of Vanex

TECHNICAL DATA

Density (g/cm³): 1,02 kg/l

Solids content in volume: 50%

DRY TIMES BY 20° C/RH 50%

Touch dry: 15 minutes

Dry to handle: 30 minutes

Dry to recoat: N/A

Fully cured: N/A

RECOMMENDED WET FILM THICKNESS

50 µm

RECOMMENDED DRY FILM THICKNESS

25 µm

PRACTICAL CONSUMPTION

The actual consumption is dependent on the method of application.

DIRECTIONS FOR USE

- Degrease, clean, and dry the surface
- Shake Kuraltex BL 314 before use
- Dilute the product with maximally 10% water
- Apply the product very thinly using a soaper ('scrubby'), sponge, or spray gun and distribute it evenly over the surface

APPLICATION CONDITIONS

Minimum ambient temperature : 10°C

Maximum relative humidity : 90%

Minimum surface temperature : 10 °C*

Maximum surface temperature: 35 °C

* When applying a coating and during the drying phase, the surface temperature must be at least 3 °C above the dew point.

CLEANING OF EQUIPMENT / SPILLS

Rinse with clean water immediately after use.

PH

6,50

SHELF LIFE

Can be kept for a minimum of 12 months when stored in a dry, cool, and frost-free environment in the original unopened packaging.

Date issued: 09/12/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu