



NANOSIGN® COATEX GRUNDIERUNG EP

Adhesive primer for the NanoSign® Coatex Non-Stick system

- Excellent adhesion
- Quick drying and curing
- Okay to repaint
- Usable on a variety of surfaces
- Easy to sand

NANOSIGN® COATEX GRUNDIERUNG EP

BESCHREIBUNG

A two-component epoxy adhesive primer for the NanoSign ® Coatex Non-Stick system and as an adhesive primer for 9600 Rust-O-Thane.

EMPFOHLENE VERWENDUNG

NanoSign®-Coatex Primer EP is a universal Epoxy adhesive primer for all surfaces, preferably as an adhesive primer in the NanoSign®-Coatex Non-Stick system and as an adhesive primer for 9600 Rust-O-Thane.

Usable on thermo-hardened plastics, metals and non-ferrous metals, and all size-holding surfaces including size-holding and dry hardwood and old paint systems.

TECHNISCHE DATEN

Feststoffgehalt in Gewicht: 68%
Feststoffgehalt in Volume: 50%

PRAKTISCHE ERGIEBIGKEIT

The actual consumption is dependent on the roughness of the surface.

HINWEISE ZUR VERARBEITUNG

Clean the surface with Grease Cleaner Foam, and, if needed, roughen by sanding it and then remove all dust.

Remove any release agent present from thermo-hardened plastics.

(make a test piece using Grafitex 3 or 4)

Thoroughly blend the two components until you have a homogeneous mass and apply with an appropriate tool until you have a smooth uniform layer. The coverage does not need to be perfect.

When repairing powder coatings, the dry layer thickness must be at least 50 microns.

Finish after 16 hours, but within 24 hours, using a NanoSign component or another suitable Prochemko product.

Brush: Dilute 5% to 10% with Coatex Special Thinner.

Roller: Dilute 5% to 10% with Coatex Special Thinner and apply with a short-haired perlon or microfibre roller.

Airless: dilute maximally to 5% with Coatex Special Thinner.

Nozzle opening 0.013 to 0.015 inches.

Spray angle 50 to 60°

Pressure 150 to 200 bar

ANWENDUNGSBEDINGUNGEN

Minimum ambient temp. : 10 °C

Maximum ambient temp. : 30 °C

Minimum surface temp.: 10 °C (3 °C above the dew point)

Maximum humidity : 85%

BEMERKUNGEN

Appearance of dry layer: Matt layer; insufficient cover with some colours.

Drying is based on an ambient temperature of approx. 20 °C.

Colour: Grey; some RAL colours are available when ordering.

Contact the Prochemko inside sales department for the applicable conditions.

LAGERFÄHIGKEIT

Can be kept for 12 months when stored in the unopened original package in a dry environment at a temperature between 10 °C to 35 °C.

Ausgabedatum: 22/02/2021

Verfügbare Farben und Packungsgrößen: Bitte beziehen Sie sich auf die jeweilige Produktseite auf www.rust-oleum.eu für eine Übersicht der aktuell verfügbaren Farben und Größen verpacken.

Haftungsausschluss: Die hierin enthaltenen Informationen wurden nach bestem Wissen wahrheitsgetreu und präzise und im guten Glauben zusammengestellt. Wir übernehmen aber keine Haftung. Wir gehen davon aus, dass sich der Anwender eigenverantwortlich über die Eignung unserer Produkte für seine individuelle Zweckbestimmung informiert hat. Rust-Oleum Europe übernimmt keinerlei Haftung für Folgeschäden oder mittelbare Schäden. Die Produkte müssen gelagert, gehandhabt und unter Bedingungen verwendet werden, die den Empfehlungen von Rust-Oleum Europe entsprechen, die in der neuesten Ausgabe des Produktdatenblatts angegeben sind. Der Anwender muss sicherstellen, dass er die neueste Ausgabe besitzt. Die neuesten Ausgaben des Produktdatenblatts können kostenlos auf www.rust-oleum.eu heruntergeladen oder bei unserer Kundendienstabteilung angefordert werden. Rust-Oleum Europe behält sich das Recht vor, die Eigenschaften seiner Produkte ohne vorherige Ankündigung zu ändern.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu