



# **NANOSIGN® COATEX SHIELD**

# 2K durable anti-graffiti coating

- · Dirt repelling and easy to clean
- · Excellent hardness, scratch and wear resistant
- · Excellent adhesion on a wide variety of surfaces
- Exceptional resistant to chemicals and solvents

# **NANOSIGN® COATEX SHIELD**

#### DESCRIPTION

A two-component coating based on nanotechnology (polyether siloxanes with UV additives). Particularly suitable for surfaces requiring durable protection against atmospheric influences and graffiti.

#### RECOMMENDED USE

NanoSign-Coatex Shield is a durable protection system resistant to atmospheric influences. Suitable surfaces: bare and coated anodised metals, stainless steel, solid core sheets, and coated surfaces.

Very suitable as an anti-graffiti coating due to its superb chemical and solvent resistance. Do not use on thermoplastic and epoxy surfaces.

# **TECHNICAL DATA**

Density (g/cm³): 1,0 kg/l Gloss Level: Gloss Solids content in volume: 60%

Mixing Ratio: Basis: Hardener = 4: 1 (volume)

# DRY TIMES BY 20° C/RH 50%

Touch dry: 3 hours
Dry to handle: 3 hours
Dry to recoat: 16 hours
Fully cured: 7 days
Pot Life: 3 hours (20°C)

#### RECOMMENDED WET FILM THICKNESS

25 - 35 µm

# RECOMMENDED DRY FILM THICKNESS

 $15 - 22 \, \mu m$ 

#### THEORETICAL CONSUMPTION

With a dry film thickness of 15  $\mu$ m: 40 m<sup>2</sup> / liter

# PRACTICAL CONSUMPTION

The actual consumption is dependent on the surface and the application method.

#### **DIRECTIONS FOR USE**

Apply NanoSign-Coatex Shield to a dry, clean, grease-free, and dirt-free surface in a closed layer

Apply the product using a brush, spray gun, or short-haired roller.

Apply in one treatment, see also consumption.

Vigorously mix A and B components in the correct proportion until a homogeneous mixture is obtained.

Do not dilute NanoSign-Coatex Shield.

#### REMOVE GRAFFITI

Topper and/or Topper Gel

#### HVI P

Pressure: As provided by the system Nozzle opening: 0.8 to 1.0 mm Visc: ready-to-use, do not dilute

Pressure: 2 to 3 bar

Nozzle opening: 0.8 to 1.1 mm Visc: ready-to-use, do not dilute

#### Air mix

Material pressure: 100 to 150 bar Atomising pressure: 2 to 4 bar Nozzle opening: 0.031 to 0.025 inches Visc: ready-to-use, do not dilute.

# **APPLICATION CONDITIONS**

Minimum ambient temperature : 10°C Maximum relative humidity : 80% Minimum surface temperature : 10°C Maximum surface temperature: 35 °C

### **CLEANING OF EQUIPMENT / SPILLS**

Isopropyl Alcohol with thinner if dried out.

## **SAFETY DATA**

 VOC level:
 275 g/l

 VOC category:
 A/j

 VOC limit:
 500 g/l

# SHELF LIFE

Can be kept for a minimum of 12 months from the date of delivery when stored in a dry environment at a temperature between 0  $^{\circ}$ C and 30  $^{\circ}$ C in the unopened original packaging.

**Date issued:** 05/02/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V. Zilverenberg 16 5234 GM 's-Hertogenbosch The Netherlands T:+31 (0) 165 593 636 F:+31 (0) 165 593 600 Tor Coatings Ltd (Rust-Oleum In Shadon Way, Portobello Ind. Estate Birtley, Chester-Ie-Street DH3 2RE United Kingdom T: +44 (0)1914 113 146 F: +44 (0)1914 113 147 info@rust-oleum.eu Rust-Oleum France S.A.S. 38, av. du Gros Chêne 95322 Herblay France T: +33(0) 130 40 00 44 F: +33(0) 130 40 99 80 N.V. Martin Mathys S.A. Kolenbergstraat 23 3545 Zelem Belgium T: +32 (0) 13 460 200 F: +32 (0) 13 460 201 info@rust-oleum.eu