



KARSTEN TUBE

Checking surfaces with hydrophobic treatment

- Shows the result of your work to your customers
- Measuring is knowing
- For all stone surfaces
- Fixes water absorption before and after hydrophobic sealing

KARSTEN TUBE

DESCRIPTION

A tool to determine the porosity and/or water absorption behaviour of all stone surfaces. We recommend you use it before and after making surfaces hydrophobic.

UTILISATION RECOMMANDÉE

According to Dr Karsten, the testing of water absorption through mineral constructions materials using the test tube provides the exact construction material data, respectively a building section, with respect to the moisture absorption, where it indicates the amount of water passing through the construction material (air dry at the start).

The test tube is supplied as a vertical model.

The method can be used both in practice and in the laboratory.

SYSTÈME RECOMMANDÉ

Use elastic putty to stick the test tube to façade or wall to be tested.

To this end, the putty is rolled up into a roll beforehand and laid on the rim of the tube.

Pressing the tube onto the surface causes the putty to create a watertight adhesion.

During the testing, lightly press on the tube so that the putty does not sag, which would lead to incorrect data.

The contact area of the water with the surface must be minimally 1 cm².

To test the water absorption capacity, fill the test tube using a plastic laboratory spray bottle or similar.

The amount of water penetrating is read off at regular intervals.

The test must be carried out at different places to achieve a representative picture of the total surface.

In the case of a brick façade, carry out tests on the entire brick as well as on the connection points of bed and perpend joints of the building brick.

For non-porous surfaces, such as concrete, carry out the tests on places that provide a geometric distribution for the entire surface.

30 mm filling height = stripe	4.0	= water pressure at wind speed	83.5 km/h
40 mm	3.5		92
50 mm	3.0		102
92 mm	1.0		135
113 mm	0.0		155

The impregnated façade function (reduction of the water absorption) is determined to be adequate when the water column drops max. 0.2 ml during the two-minute test period and fills up 40 mm (stripe 3.5 in driving rain), i.e. the water column drops by two stripes.

Date d'émission: 22/11/2021

Couleurs et conditionnements disponibles: Reportez-vous à la page produit concernée sur www.rust-oleum.eu pour avoir un aperçu des couleurs et des tailles d'emballage actuellement disponibles.

Notion de responsabilité: Les informations communiquées ici sont véridiques et exactes et sont fournies de bonne foi au meilleur de nos connaissances, mais sans garantie. Il est estimé que l'utilisateur se sera assuré lui-même de la compatibilité de nos produits avec son usage particulier. Rust-Oleum Europe ne sera en aucun cas tenue pour responsable quant aux dommages consécutifs ou indirects. Les produits doivent être stockés, manipulés et appliqués conformément aux conditions respectant les recommandations de Rust-Oleum Europe détaillées dans le dernier exemplaire de la fiche technique du produit. Il incombe aux utilisateurs de veiller à disposer de l'exemplaire actuel. Les dernières versions de la fiche technique du produit sont disponibles gratuitement et peuvent être téléchargées sur www.rust-oleum.eu ou sur demande adressée à notre département Service à la clientèle. Rust-Oleum Europe se réserve le droit de modifier les propriétés de ses produits sans avis préalable.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu