

PROCHEMKO



ZYLOX

Anti-graffiti coating for porous surface/floor impregnation

- Water and oil repellent
- Long working
- Virtually invisible after drying
- UV and chemicals resistant
- Water permeable, which prevents frost damage

WWW.PROCHEMKO.EU

ОПИСАНИЕ

A permanent anti-graffiti coating / impregnator based on fluoropolymers with strong hydrophobic and oleophobic properties. Suitable for untreated masonry, concrete, mineral plaster and natural stone tiles, such as: sandstone, terrazzo, limestone, bluestone, granite etc.

ПРЕПОРЪЧИТЕЛНА УПОТРЕБА

It is an anti-graffiti coating and impregnating agent with hydrophobic and oleophobic properties for untreated masonry, concrete, mineral plaster and natural stone tiles, such as: sandstone, terrazzo, limestone, bluestone, granite etc.

ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см³): 1,0 kg/l
Гланцово ниво: Мат
Съдържание на сухо вещество (по обем): 10%

ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир: 1 hour
Готов за повторно нанасяне: 1 hour
group_dry_40_full_cure: 3 - 4 days

РАЗХОДНА НОРМА

ANTI-GRAFFITI: 3 - 5 m²/L in a two layer system until saturation of the substrate is reached. Consumption strongly depends on the application method and type of substrate.
IMPREGNATOR: 10 - 20 m²/L. Consumption strongly depends on the absorbency of the substrate.

КОНСУМАЦИЯ

Consumption is heavily dependent on the condition and absorptive capacity of the surface.

НАЧИН НА УПОТРЕБА

The surfaces to be treated must be wind dried, dustless, and free of grease.

Do not apply in direct sunlight or on hot surfaces.

Stir or shake the Zylox well before use.

ANTI-GRAFFITI: Use product as supplied. Apply in two coats wet-on-wet with a maximum drying time of 30 minutes between the two layers, depending on the conditions and the surface. Apply using brush, roller or flow-coat system (low pressure avoiding mist formation). Avoid oversaturation.

IMPREGNATOR: Dilute Zylox with water 1:1. Apply the product in 1 layer, make sure the substrate is saturated, avoid leaving a residue on the surface. Use a (wide) brush or soaper. Make sure the equipment is free of solvents.

УСЛОВИЯ ЗА НАНАСЯНЕ

Minimum ambient temperature : 5 °C
Maximum relative humidity : 70%
Minimum surface temperature : 5 °C
Maximum surface temperature: 25 °C

ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

Rinse with water immediately after use.

ЗАБЕЛЕЖКИ

Remnants of this product should be treated as chemical waste and may not be disposed of together with commercial or household waste.

Treat empty packaging as industrial waste unless well cleaned and dry.

Do not dispose of clean packaging as chemical waste.

ДАНИИ ЗА БЕЗОПАСНОСТ

Ниво на ЛОС: 51 g/l
Готов за употреба ЛОС (VOC Readymix): 51 g/l
Категория ЛОС: A/i
group_voc_40_limit: 140 g/l

PH

5

СРОК НА ГОДНОСТ

Can be kept for a minimum of 12 months when stored in a dry, cool, and frost-free environment in the original unopened packaging.

Дата на издаване: 07/10/2025

Налични цветове и размери на опаковките: Моля, вижте съответната продуктова страница на www.rust-oleum.eu, за да се запознаете с актуалните налични цветове и размери на опаковките.

Отказ от отговорност: Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от www.rust-oleum.eu или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu