

PROCHEMKO



ZYLOX

Anti-graffiti coating for porous surface/floor impregnation

- Water and oil repellent
- Long working
- Virtually invisible after drying
- UV and chemicals resistant
- Water permeable, which prevents frost damage

WWW.PROCHEMKO.EU

DESCRIPTION

A permanent anti-graffiti coating / impregnator based on fluoropolymers with strong hydrophobic and oleophobic properties. Suitable for untreated masonry, concrete, mineral plaster and natural stone tiles, such as: sandstone, terrazzo, limestone, bluestone, granite etc.

RECOMMENDED USE

It is an anti-graffiti coating and impregnating agent with hydrophobic and oleophobic properties for untreated masonry, concrete, mineral plaster and natural stone tiles, such as: sandstone, terrazzo, limestone, bluestone, granite etc.

TECHNICAL DATA

Density (g/cm³): 1,0 kg/l
Gloss Level: Matt
Solids content in volume: 10%

DRY TIMES BY 20° C/RH 50%

Touch dry: 1 hour
Dry to recoat: 1 hour
Fully cured: 3 - 4 days

THEORETICAL CONSUMPTION

ANTI-GRAFFITI: 3 - 5 m²/L in a two layer system until saturation of the substrate is reached. Consumption strongly depends on the application method and type of substrate.
IMPREGNATOR: 10 - 20 m²/L. Consumption strongly depends on the absorbency of the substrate.

PRACTICAL CONSUMPTION

Consumption is heavily dependent on the condition and absorptive capacity of the surface.

DIRECTIONS FOR USE

The surfaces to be treated must be wind dried, dustless, and free of grease.
Do not apply in direct sunlight or on hot surfaces.
Stir or shake the Zylox well before use.
ANTI-GRAFFITI: Use product as supplied. Apply in two coats wet-on-wet with a maximum drying time of 30 minutes between the two layers, depending on the conditions and the surface. Apply using brush, roller or flow-coat system (low pressure avoiding mist formation). Avoid oversaturation.
IMPREGNATOR: Dilute Zylox with water 1:1. Apply the product in 1 layer, make sure the substrate is saturated, avoid leaving a residue on the surface. Use a (wide) brush or soaper. Make sure the equipment is free of solvents.

APPLICATION CONDITIONS

Minimum ambient temperature : 5 °C
Maximum relative humidity : 70%
Minimum surface temperature : 5 °C
Maximum surface temperature: 25 °C

CLEANING OF EQUIPMENT / SPILLS

Rinse with water immediately after use.

REMARKS

Remnants of this product should be treated as chemical waste and may not be disposed of together with commercial or household waste.
Treat empty packaging as industrial waste unless well cleaned and dry.
Do not dispose of clean packaging as chemical waste.

SAFETY DATA

VOC level: 51 g/l
VOC readymix: 51 g/l
VOC category: A/i
VOC limit: 140 g/l

PH

5

SHELF LIFE

Can be kept for a minimum of 12 months when stored in a dry, cool, and frost-free environment in the original unopened packaging.

Date issued: 05/02/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu